HEIDELBERGCEMENT



HEIDELBERGCEMENT INDIA LTD, AMMASANDRA TEST REPORT FOR MYCEM

REF.: HCIL/QA/2019/48 DATE: 02.01.2020

HCIL(AMS)-QCD-F026

WEEK NO. : 48 11/26/2019 to 12/2/2019

CHARACTERISTIC	RESULTS OBTAINED	REQUIREMENT OF IS455:2015
(A) CHEMICAL COMPOSITION		
(i) Magnesia (MgO), % by mass	5.05	10.0 Maximum
(ii) Insoluble Residue, % by mass	0.90	4.0 Maximum
(iii) Sulphuric Anhydride (SO ₃) % by mass	2.32	3.5 Maximum
(iv) Sulphide Sulphur (S)	0.30	1.5 Maximum
(v) Loss on Ignition % by mass	2.13	5.0 Maximum
(vi) Total Chloride (CI), % by mass	0.0426	0.10 Maximum
(B) PHYSICAL TESTING		
1. Fineness of Cement		
Sp.Surface blaine (m²/Kg)	340	225 m²/kg minimum
2. Soundness		
Le-Chatelier Expansion (mm)	1.0	10 mm Maximum
Autoclave Expansion (%)	0.10	0.8 % Maximum
3. Setting Time		
Initial (in Minutes)	105	Not less than 30 minutes
Final (in Minutes)	210	Not more than 600 minutes
4. Compressive Strength (MPa)		
(a) At 72 ± 1 Hrs.	23.4	16 MPa Minimum
(b) At 168 ± 2 Hrs.	33.6	22 MPa Minimum
(c) At 672 ± 4 Hrs.	53.0	33 MPa Minimum

Remarks :

- 1. Physical Lab Temperature during testing $-27 \pm 2^{\circ}$ C
- 2. Portland Slag Cement conforms to the requirement of IS 455:2015 in all respects.

Mgr (QC)